

How To Make Silver Clay Jewelry

How To Make Silver Clay Jewelry

Downloaded from remodelicious.com by Laylah & Cross

INTRODUCTION TO SILVER CLAY JEWELRY MAKING

Silver clay jewelry has opened a world of creative possibilities for both seasoned metalsmiths and complete beginners. Unlike traditional silversmithing that requires soldering, sawing, and heavy tools, silver clay—also known as precious metal clay (PMC)—allows you to mold, roll, and shape silver much like you would with polymer clay or ceramic clay. Once fired in a kiln or with a torch, the binder burns away, leaving behind a piece that is 99.9% pure silver. If you have ever wondered **how to make silver clay jewelry**, you are about to discover a rewarding craft that combines artistic expression with the satisfaction of creating heirloom-quality pieces. This guide will walk you through every step, from selecting the right materials to finishing your first pendant, ring, or pair of earrings.

WHAT IS SILVER CLAY?

Silver clay is composed of microscopic particles of pure silver suspended in an organic binder and water. The binder gives it a clay-like consistency that can be shaped, textured, and sculpted. When heated to a high temperature, the binder burns away and the silver particles sinter—fusing together into a solid metal object. The result is a piece that is chemically identical to fine silver (999). There are several brands and types, including PMC (Precious Metal Clay), Art Clay Silver, and various fast-fire formulations. Some require a kiln, while others can be fired using a handheld torch. Understanding the differences is a key part of learning **how to make silver clay jewelry** successfully.

Types of Silver Clay

- **PMC3 and Art Clay Silver 650:** Low-temperature clays that can be fired at around 1200°F to 1300°F, making them compatible with some torch firing methods.
- **PMC+ and Art Clay Silver 700:** Medium-temperature clays that require a kiln firing at approximately 1470°F. They offer a good balance of workability and shrinkage.
- **PMC Flex and Art Clay Slow Dry:** These versions stay workable for longer periods, making them ideal for intricate designs or humid climates.
- **Syringe and Paste forms:** Used for adding details, repairs, or attaching elements. They can also be applied as slip (like glue) to join wet or dry clay pieces.

Each type has a slightly different shrinkage rate (typically 10-20%), so it is essential to design your piece with that final size in mind.

TOOLS AND MATERIALS YOU WILL NEED

Before diving into the creative process, gather the essential tools. Many of these are common household or basic craft items, but a few are specific to metal clay work.

Basic Tool List

- **Silver clay:** Start with a 20g to 50g package of PMC3 or Art Clay Silver 650 for torch firing.
- **Non-stick work surface:** A Teflon sheet, ceramic tile, or glass work mat prevents sticking.
- **Rolling tools:** Acrylic rod or rolling pins with thickness guides (cards or plastic strips) to achieve uniform thickness.
- **Shaping tools:** Clay sculpting tools, toothpicks, cocktail sticks, and silicone-tipped tools for smoothing.
- **Texture items:** Fabric, lace, leaves, rubber stamps, or texture plates to imprint designs.
- **Cutters and shapes:** Small cookie cutters, circle templates, or craft knives for precise shapes.
- **Drying equipment:** A food dehydrator or a low-temperature oven (around 200°F) to speed up drying, or simply leave pieces overnight.
- **Sanding supplies:** Fine-grit sandpapers (400 to 1200 grit), emery boards, and micro-mesh pads for polishing.
- **Firing tool:** Either a kiln with a programmable controller or a butane/map torch (for torch-fire clays) and a fire brick or kiln shelf.
- **Finish tools:** Brass brush, polishing cloth, burnisher, and optional liver of sulfur for patina.

Having these items ready ensures a smooth workflow when you start your first project.

STEP-BY-STEP GUIDE: HOW TO MAKE SILVER CLAY JEWELRY

Now let's walk through the entire process from start to finish. For this example, we will create a simple textured pendant that can be torch-fired. As you become more comfortable, you can adapt these steps for rings, earrings, and more complex designs.

Step 1: Conditioning the Clay

Take your silver clay out of its sealed package. It may feel dry or crumbly if it has been stored improperly. To condition it, knead the clay between your fingers until it becomes soft, pliable, and uniform. If it cracks, add a drop of distilled water and work it in. The goal is a smooth, hydration level

that allows easy rolling without sticking. Some beginners find that **how to make silver clay jewelry** is easier if they start with a small 10g piece to practice.

Step 2: Rolling and Shaping

Place the clay on your non-stick surface. Use rolling guides (two acetate strips or cardstock of desired thickness, usually 3-4mm for pendants) to ensure even thickness. Roll with an acrylic rod until the clay is level with the guides. Too thin a piece may break during firing; too thick may shrink unevenly. Now you can cut your basic shape. Use a cookie cutter or trace a template with a craft knife. Remove excess clay and save it in an airtight bag for later use.

Step 3: Adding Texture and Details

Before the clay dries, press texture into the surface. Lightly dust your texture item with a bit of cornstarch or oil to prevent sticking. Roll over it with gentle pressure to imprint the pattern. You can also carve lines with a toothpick, add dots with a stylus, or attach small rolled clay balls for a 3D effect. To attach separate pieces, moisten both surfaces with slip (water mixed with a tiny bit of clay). Smooth seams with a soft brush or your fingertip moistened with water.

Step 4: Drying the Clay

Metal clay must be completely dry before firing. If you fire damp clay, trapped steam can cause it to crack or explode. Allow your piece to air-dry on a ceramic tile or paper towel for several hours or overnight. For faster results, use a dehydrator set to 130°F (55°C) for 30 minutes to an hour. The piece should feel hard and sound like ceramic when tapped. It should also appear chalky white or pale gray. If you notice any cracks or rough edges, sand them now with a fine file or sandpaper while it is still in the dry (green) state.

Step 5: Sanding and Refining the Dry Piece

Once dry, your piece is fragile but can be sanded and shaped like plaster. Use 400-grit sandpaper to smooth edges and remove fingerprints. For deeper scratches or uneven areas, start with a lower grit (300) and progress to 600 or 800. You can also drill holes for jump rings or earring posts using a small drill bit (handheld or Dremel). Be gentle—too much pressure will break the dry clay. This is your last chance to perfect the design because after firing, the metal will be harder and less forgiving.

Step 6: Firing the Silver Clay

Firing transforms the fragile clay into solid silver. The exact method depends on your clay type.

- **Kiln firing:** Place your piece on a kiln shelf with a small ceramic fiber blanket or kiln paper underneath. Program the kiln to ramp up slowly to the recommended temperature (e.g., 1470°F for PMC+) and hold for 10–30 minutes. Then allow to cool naturally.
- **Torch firing (for torch-fire clays like PMC3 or Art Clay Silver 650):** Position your piece on a fire brick. Heat gently from a distance to warm the binder, then bring the torch closer until the piece glows cherry red. Keep the flame moving evenly over the piece for 2–4 minutes. The binder will burn off with a small flame or smoke. Let it cool to room temperature before handling.

After firing, the piece will appear white or frosted due to the sintered silver surface. Do not worry—this is normal and will be polished away.

Step 7: Post-Fire Finishing and Polishing

Now your piece is solid silver! Use a brass brush with water and a little dish soap to scrub off the white oxidized layer. Brush in one direction until you see a matte silver sheen. For a high-polish finish, use a burnishing tool, a steel burnisher, or a polishing cloth (silver cloth). You can also use a rotary tool with a felt buffing wheel and a polishing compound like rouge. If you desire a dark patina in the crevices, apply liver of sulfur (diluted in hot water) using a brush or dip, then rinse and polish the raised areas.

Step 8: Final Assembly

Attach a jump ring to the hole you drilled, add a chain or leather cord, and your piece is complete. For earrings, glue earring posts with epoxy or attach findings. Congratulations—you now know **how to make silver clay jewelry** from start to finish!

TIPS FOR BEGINNERS

- Start with small, simple shapes. Avoid complex multi-part assemblies until you understand shrinkage and firing behavior.
- Maintain consistent hydration. Keep unused clay in an airtight container with a damp paper towel (not touching the clay) to prevent drying.
- Use slip like glue. Always moisten surfaces before joining wet or dry clay to avoid breakage.
- Practice on a test piece. Fire a small scrap first to see how your chosen clay responds to your kiln or torch.
- Work in a well-ventilated area during firing. Burned binders release small amounts of organic

vapor, so use a fume hood or open windows.

- Keep a notebook. Record thickness, firing temperature, hold time, and shrinkage for each project. This will help you refine your technique.

COMMON MISTAKES AND HOW TO AVOID THEM

1. **Cracking during drying or firing** – Usually caused by uneven thickness, rapid drying, or insufficient moisture. Slow down the drying process and keep your clay consistently hydrated during shaping.
2. **Bubbles or blisters after firing** – These occur if the clay was not fully dry. Ensure your piece is bone dry, especially if it is thick. Use a dehydrator for large pieces.
3. **Piece is too fragile after firing** – This may be due to insufficient sintering. Check that your firing temperature and hold time match the clay specifications. Also, ensure uniform thickness—thin sections may break easily.
4. **Shrinkage surprises** – Remember that silver clay shrinks 10-20%. Design your piece larger than the final size. For a ring, make it 2-3 ring sizes larger before firing.

5. **Sticking to the work surface** – Dust your surface with a tiny amount of olive oil or use a dedicated non-stick mat. Avoid adding too much water to the clay.

EXPLORING ADVANCED TECHNIQUES

Once you are comfortable with the basics, you can expand your skills. Try embedding lab-created gemstones (check temperature tolerance), creating hollow forms using combustible cores, combining silver clay with fine silver wire for intricate details, or making multi-part hinged pieces. You can also experiment with different textures like woven fabrics, leaves, or even laser-engraved patterns. The key is to keep learning and testing. Many online communities and workshops share tips on **how to make silver clay jewelry** with advanced results.

CONCLUSION

Learning **how to make silver clay jewelry** is an accessible and deeply satisfying craft that blends the tactile joy of working with clay with the timeless beauty of precious metal. With the right tools, a bit of patience, and a willingness to experiment, you can create custom pendants